

Vendor -Plant: 0100 -No: 91001108
SEISSCHWIMDT GmbH
Daimlerstr. 11
D-58840 PLETTERNBERG
DEUTSCHLAND

Receiver -Plant: 100 -No: 14550700
Magna PT S.p.A.
Via dei Ciclamini, 4
Zona Industriale
I-70026 MODUGNO

Unloading Area: 14248
place of storage:
Consumption:
Dispatch Type:
Forw. Agent Name:
-Number:
Gross Weight:

Truck Company
Schweitzer GmbH & Co.
16070077
24.217 KG

VAT-No.: DE123840478
VAT-No.: IT04886850728

ASN-No -Pos Sup. Ref. No. Cust. Quant. UM V/G Name of delivery Purch. Ord. Nr.
-Date Suppl. Ref. No. Vend. Add. Data Vendor
Pack. Mat. -Quant. -Number Cust. -Number Vendor Consignment

80681270	000010	2511108490	12.190	PC	S	ZAHNRAD 2.GANG	550003916202
02.12.2019		035309-900		PC	S	25 mo 84 R0	nt. wt.: 20.317 KG , gr. wt.: 22.278 KG
165453		CC: 190110062	530	PC	S	KUEHNEN+NAGEL S.r.l.	
		CC: 190110055	530	PC	S	ACCETTAZIONE MERCE	
		CC: 190110045	530	PC	S	Quantità dichiarata: 12180	
		CC: 190110037	530	PC	S	Quantità effettiva:	
		CC: 190110030	530	PC	S	Tipo Imballaggio:	
		CC: 190110025	530	PC	S	Quantità Imballi: 23	
		CC: 190110012	530	PC	S	Conformità alle schede d'imballo:	
		CC: 190110002	530	PC	S	Data controllo: 11/12/2019	
		CC: 190109992	530	PC	S	Firma	
		CC: 190109982	530	PC	S		
		CC: 190109975	530	PC	S		
		CC: 190109967	530	PC	S		
		CC: 190109961	530	PC	S		
		CC: 190109955	530	PC	S		
		CC: 190109948	530	PC	S		
		CC: 190109936	530	PC	S		
		CC: 190109931	530	PC	S		
		CC: 190109923	530	PC	S		
		CC: 190109917	530	PC	S		
		CC: 190109909	530	PC	S		
		CC: 190109899	530	PC	S		
		CC: 190109890	530	PC	S		
		CC: 190109886	530	PC	S		
		CC: 23	DCT300	PC			
		Cast-Number: 247303					
		UC-Material: G082230030					
		Text: Engineering Change Status A					
		Text: Customer Change No.					
		Text: Supplier Index -					

80683546 000010 2511109390 3.700 PC M SCHALTRAD 7.GANG 550003915702
02.12.2019 035307-900 1.850 PC M 180251686 nt. wt.: 1.769 KG , gr. wt.: 1.939 KG
165454 CC: 190109958

Quant. Check: 500 PP76660 Rating Check:



SEISSENSCHMIDT GmbH, Postfach 1520, D-58815 Plettenberg

Company
Magna PT S.p.A.
Via dei Ciclamini, 4
Zona Industriale
I-70026 Modugno

Artikel ZAHNRAD 2.GANG
(Part name: / Désignation pièce)
Kd.-Zg.-Nr. 251.1.1084.90
(customer part number / No. du plan client)
Kd.-Auftr.-Nr. 30002077
(order no. / No. De commande)
Schmelzen-Nr. 247303
(heat number / No. de coulée)
Werkstoff 20MnCRS5
(steel grade / Qualité)

HBS-Teile.-Nr. 035309-900
(HBS-Part number: / N° du plan HBS)
Änderungsindex A
(draw. notific. index / Indice du plan)
Lieferschein-Nr. 80681270/000010
(shipping advice no. / Bulletin de livraison)
Schmelzen-Knz.
(heat code / Repère de coulée)
Herstellprozess E/A/K.
(process flow / Procédé fabrication)

Auftrag 1021036
(order no./ordre no.)
SAP UC-Material G082230030
(SAP UC-material/SAP UC-material)
Lieferdatum 11/21/2019
(shipping date / Date de livraison)

Stückzahl 12,190
(quantity / Quantité)

Stahlhersteller Georgsmarienhütte GmbH
(steel mill / Acierrie)
Lieferspezifikation GCG_805000_02
(technical specification / Spécification de livraison)

Gießformat 245X245
(casting dim. / Dimension coulée)
Lieferzustand +FP Gießen isotherma
(delivery condition / Etat de livraison)

Rohmat.-abm. 55 Rund
(raw material dim. / Barre diamètre)
Umformgrad 25-FACH
(Diameter / diamètre)

Schmelzeanalyse (cast analysis / Analyse de coulée)

%C	%Si	%Mn	%P	%S	%Cr	%Mo	%Ni	%Cu	%Sn	%Al	%V	%B	%Ti	%Nb	%W	%Co	%Sb	%As	%Pb	%Te	%Ca	%N	ppm H	ppm O
0.2100	0.1000	1.2500	0.0110	0.0210	1.1900	0.0500	0.1700	0.1500	0.0090	0.0320	0.0070	0.0003	0.0010	0.0080	0.0000	0.0000	0.0010	0.0060	0.0008	0.0000	0.0006	0.0110	1.9000	7.0000

Härtbarkeit (hardenability / valeurs de trempabilité)

mm	1	1.5	2	3	4	5	6	7	8	9	10	11	13	15	20	25	30	35	40	45	50		
HRC	0.00	46.10	0.00	45.40	0.00	44.60	0.00	41.80	0.00	38.50	0.00	36.30	34.40	33.20	0.00	0.00	0.00	0.00	0.00	0.00	0.00		
Fdyn	0.00	-	0.00																				
								DI-Wert (DI value / diamètre idéal)		0.00													

Metallographische Prüfungen (metallographical test / Examens métallographiques)

Gefüge (part name / Désignation pièce)	FERRIT-PERLIT					Randentkohlung (decarburation / Décarburation)			0.000	
Korngröße (grain size / grosseur de grain)	Prim.	5	-	8	Sek.	7	-	9		

Mechanische Eigenschaften (mechanical properties / propriétés mécaniques)

RM (N/mm ²)	Rp0.2(N/mm ²)	
0.00	-	0.00

A(%)	Z(%)
0.00	-
-	0.00

Oberflächenhärte (surface hardness / dureté superficielle)

Vorschrift (specification / Spécification)	152.0	-	201.0	HBW
Ergebnis (result / Résultat)	0	-	0	170.0

Kernhärte (core hardness / dureté centre)

Vorschrift (specification / Spécification)	0.00	-	0.00
Ergebnis (result / Résultat)	0.00	-	0.00

Einsatzhärtungstiefe (case hardening depth / cémentation gravité)

AV(J)	bei T(°C)
0.00	-
-	0.00

Vorschrift (specification / Spécification)	0.00	-	0.00	mm
Ergebnis (result / Résultat)	0.00	-	0.00	mm

Reinheitsgrad (degree of purity / Degré de Pureté)	K3=0
---	------

