

EDI - ASN Note
(VDA 4912)

Vendor

-Plant: 0100
-No: 91001108
Linamar Plettenberg GmbH
Daimlerstr. 11
58840 PLETTENBERG
DEUTSCHLAND

Receiver

-Plant: 100
-No.: 14550700
Magna PT S.p.A.
Via dei Ciclamini, 4
Zona Industriale
I-70026 MODUGNO

Unloading Area: 14248
place of storage:
Consumption:
Dispatch Type: Truck Company
Forw. Agent Name: Schweitzer GmbH & Co.
-Number: 16070077
Gross Weight: 21.997 KG

Load-No.: 113285

20.09.2023 - 15:27
page 3/3

VAT-No.: DE123840478

VAT-No.: IT04886850728

ASN-No	-Pos	Sup. Ref. No. Cust.	Quant.	UM	V/G	Name of delivery	Purch. Ord. Nr.
-Date	Suppl. Ref. No. Vend.					Add. Data Vendor	
	Pack. Mat. -Quant.		- Number Cust.			-Number Vendor	Consignment

CC: 4,000
Cast-Number: 641732
UC-Material: L015288X10
Text: Engineering Change Status a
Text: Customer Change No. C0_21_002676-01
Text: Supplier Index -

TBA-500256PCDCT300/P01850

811268300000102511123290035540-900
20.09.2023

180350344

5012865523

1.850PCSCHALTRAD 7.GANG

1.850PCS

TBA-500256PCDCT300/P01850

550004564101
nt. wt.: 716 KG , gr. wt.: 802 KG

335401

***** E N D *****

KUENNE+NAGEL S.r.l.
Via dei Ciclamini, SNC - 70026 Modugno (BA)

27/SET 2023

"Ricevuto con riserva di
verifica su qualità e quantità"

GR:

Quant. Check:

Rating Check:

Abnahmezeugnis 3.1 EN 10204 (Test certificate: / Certificat:)

Unimar Plattenberg GmbH, Postfach 1520, D-58815
Plattenberg

Company
Magna PT S.p.A.
Via dei Ciclamini, 4
Zona Industriale
I-70026 Modugno



Artikel SCHALTRAD 7.GANG
(Part name / Désignation pièce)
Kd.-Zg.-Nr. 251.1.1.1232.90
(Customer part number / No. du plan client)
Kd.-Auftr.-Nr. 30005430
(Order no. / No. De commande)
Schmelzen-Nr. 278154
(Heat number / No. de Coulee)
Werkstoff 20MNCRS5
(Steel grade / Qualité)

HBS-Teile.-Nr. 035540-900
(HBS-Part number: / N° du plan HBS:)
Änderungsindex a
(draw. notific. index / indice du plan)
Lieferschein-Nr. 81126830/000010
(shipping advice no. / Bulletin de livraison)
Schmelzen-Knz.
(heat code / Repère de Coulee)
Herstellprozess E/VAC.
(process flow / Procédé fabrication)

Auftrag 1040558
(order no./ordre no.)
SAP UC-Material AB14589X10
(SAP UC-material/SAP UC-material)
Lieferdatum 09/07/2023
(shipping date / Date de livraison)
Stückzahl 1,850
(quantity / Quantité)
Gießformat
(casting dim. / Dimension coulee)
Lieferzustand + FP Glühen isotherma
(delivery condition / Etat de livraison)
Rohmat.-abm. 38 Rund
(raw material dim. / Barre diamètre)
Umformgrad 50
(Diameter / diamètre)

Stahlhersteller Acciaierie Bertoli Safau
(steel mill / Acierrie)
Lieferspezifikation GCG 805000_02
(technical specification / Spécification de livraison)

Schmelzanalyse (cast analysis / Analyse de coulée)

%C	%Si	%Mn	%P	%S	%Cr	%Mo	%Ni	%Cu	%Sn	%Al	%V	%B	%Ti	%Nb	%W	%Co	%Sb	%As	%Pb	%Te	%Ca	%N	ppm H	ppm O
0.1970	0.2200	1.1100	0.0110	0.0250	1.1200	0.0400	0.1100	0.2000	0.0090	0.0200	0.0040	0.0001	0.0029	0.0030	0.0000	0.0090	0.0010	0.0050	0.0001	0.0000	0.0050	0.0090	1.0000	12.000

Härtbarkeit (hardenability / valeurs de trempabilité)

mm	1	1,5	2	3	4	5	6	7	8	9	10	11	13	15	20	25	30	35	40	45	50		
HRC	0.00	45.20	0.00	44.60	0.00	42.80	0.00	39.30	0.00	35.80	0.00	33.30	31.40	30.00	27.80	26.20	0.00	0.00	0.00	0.00	0.00		
Fdyn	0.00	-	0.00																				

Metallographische Prüfungen (metallographical test / Examens métallographiques)

Gefüge (part name / Désignation pièce)	FERRIT - PERLIT	Randentkohlung (decarburation / Décarburation)	0.000
Korngröße (grain size / grosseur de grain)	Prim. 9	Sek. 0	0

Mechanische Eigenschaften (mechanical properties / propriétés mécaniques)

RM (N/mm²)	Rp0.2(N/mm²)	A(%)	Z(%)
0.00	0.00	0.00	0.00

Oberflächenhärte (surface hardness / dureté superficielle)

Vorschritt (specification / Spécification)	152.0 0	201.0 0	HBW
Ergebnis (result / Résultat)	170.0 0	185.0 0	HBW

Kernhärte (core hardness / dureté centre)

Vorschritt (specification / Spécification)	0.00	-	0.00
Ergebnis (result / Résultat)	0.00	-	0.00

Einsatzhärtungstiefe (case hardening depth / cémentation gravité)

Av(J)	bei T(°C)
0.00	0.00

Vorschritt (specification / Spécification)	0.00	-	0.00
Ergebnis (result / Résultat)	0.00	-	0.00

Reinheitsgrad (degree of purity / Degré de Pureté)	K4=0;K3=7

Datum
(date / Date)

09/20/2023

Maschinell erstellt, daher gültig ohne Unterschrift /

Computer generated, valid without signature /

Délivré par ordinateur sans

Abnahmebeauftragter / Inspector

WT - i. A. Dillmann, Johannes



23-008900

COMMERZBANK
Konto: 0501540600
BLZ: 604 800 08
IBAN: DE13 6048 0008 0501 5406 00
SWIFT: DRESDEFF604